

# 103021-K

# **AMSTAT 21**

# **Product Information**

## **Physical Properties**

#### **Carrier Resin**

Type

PE

#### Masterbatch

Specific Gravity	0.95	
Melt Index (g/10min)	7	(nominal) ASTM D1238,190°C/2.16 kg
Bulk Density (g/l)	550	(nominal)
Pellets per gram	45	(nominal)
Additive (%)	7	(nominal)

## **Regulatory Status**

Due to the wide range of application for this product regulatory information cannot be covered adequately in a technical datasheet.

Please contact <u>AsiaRegulatory@ampacet.com</u> for regulatory information.

#### Storage - Shelf Life

It is recommended to use this masterbatch within a **9**-months period. Keep the material in cool and dry place. The opened bag must be well sealed. The standard packing is 25 kg polyethylene bag on shrink wrapped hard wood pallet.


#### Comment


**AMSTAT 21** is high performance antistatic for electronic packaging which can reach surface resistivity of 10<sup>10</sup> Ohm (measured at 50%RH, 25°C) within 24 hours aging time.

The letdown ratio (LDR) depends on the thickness of the film. General recommended usage is between 2 to 4%.

The information and recommendations contained in this document are based upon data collected by Ampacet and believed to be correct. However, no warranty of fitness for use or any other guarantees or warranty of any kind, express or implied, is made to the information contained herein, and Ampacet assumes no responsibility for the results of the use of products and processes described herein. No liability whatsoever shall attach to Ampacet for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer. It is the responsibility of the buyer to ascertain that the products or processes described meet their requirements through proper trials and evaluation This is an uncontrolled document.







Note: Film samples are made with AMSTAT 21 in 30 μm LDPE Blown film Surface resistivity measured at 50%RH, 25°C

Issued:

September 2007

Revised:

March 2016